



Bay City Screw & Bolt Co.
1651 Atlantic St.
Union City, CA 94587

ALL THREAD ROD 304ss (B8)

SUBMITTAL SPECIFICATIONS

Abstract of ASTM A193

Material Grade: AISI Type 304ss, ASTM A193-B8 Cl. 1

Chemical Requirements (%)

Carbon(max):	0.08
Manganese(max):	2.00
Phosphorous (max):	0.045
Sulfur (max):	0.030
Silicon(max):	1.00
Chromium:	18.00 – 20.00
Nickel:	8.00 – 11.00

Mechanical Requirements

<u>All Diameters</u>	<u>Minimum</u>	<u>Maximum</u>
Tensile Strength (KSI)	75	
Yield Strength (KSI)	30	
Elongation in 4D (%)	30	
Reduction of Area (%)	50	
Hardness (Brinell)		223
Hardness (Rockwell)		B96

Other:

Unless otherwise specified in the purchase order, Rod shall be threaded in accordance with ANSI/ASME B1.1, Unified Inch Screw Threads, Class 2A Fit. Additional information can be found in ASTM A193/A193M – Alloy Steel and Stainless Steel Bolting Materials for High-Temperature Services.